

(19)

Europäisches Patentamt

European Patent Office

Office européen des brevets



(11)

EP 1 003 354 A1

(12)

EUROPEAN PATENT APPLICATION

published in accordance with Art. 158(3) EPC

(43) Date of publication:

24.05.2000 Bulletin 2000/21

(51) Int. Cl.⁷: **H05B 33/10**

(21) Application number: **99939247.5**

(86) International application number:
PCT/JP99/01132

(22) Date of filing: **09.03.1999**

(87) International publication number:
WO 99/46961 (16.09.1999 Gazette 1999/37)

(84) Designated Contracting States:

**AT BE CH CY DE DK ES FI FR GB GR IE IT LI LU
MC NL PT SE**

(30) Priority: **09.03.1998 JP 5721498**

(71) Applicants:

- **SEIKO EPSON CORPORATION**
Shinjuku-ku, Tokyo 163-0811 (JP)
- **MINNESOTA MINING AND MANUFACTURING
COMPANY**
St. Paul, Minnesota 55133-3427 (US)

(72) Inventors:

- **KOBAYASHI, Hidekazu,**
Seiko Epson Corporation
Suwa-shi, Nagano 392-8502 (JP)
- **SHIMODA, Tatsuya,**
Seiko Epson Corporation
Suwa-shi, Nagano 392-8502 (JP)
- **KIGUCHI, Hiroshi,**
Seiko Epson Corporation
Suwa-shi, Nagano 392-8502 (JP)


(74) Representative:

Sturt, Clifford Mark et al
Miller Sturt Kenyon
9 John Street
London WC1N 2ES (GB)

(54) METHOD OF MANUFACTURING ORGANIC EL DISPLAY

(57) Cathode instability makes patterning difficult in conventional simple matrix organic EL display devices. To solve this problem, the method for manufacturing the organic EL display device of the present invention simplifies the process and improves display performance by simultaneously patterning the cathode and transferring the light emitting layer by means of a transfer method using laser light. The use of this transfer method in the present invention allows the cathode 4 to be patterned and the light emitting layer 5 to be formed simultaneously using the laser.

Fig. 5



EP 1 003 354 A1

Description**TECHNICAL FIELD**

5 [0001] The present invention relates to method for manufacturing an organic EL display device which is used in emissive simple matrix drive-type medium or large volume monochromatic or color displays, camcorder or digital camera view finders, and the like.

BACKGROUND ART

10 [0002] The difficulty of cathode patterning in simple matrix organic EL displays has been pointed out in the past. This is because the organic layer under the cathode is readily penetrated by solvent. Cathode patterning techniques have thus far been developed to remedy such problems. Examples include the method for RGB 3-color distribution using physical masks as indicated in Japanese Patent Laid-open No.08-227276, and the method for the creation of
15 cathode partition walls for simultaneous cathode patterning during cathode deposition as indicated in US Patent 5,294,869.

[0003] As noted on page 913 of the 51st issue (September 21, 1987) of *Applied Physics Letters*, the structure of most conventional organic EL elements comprises a transparent electrode formed on a glass substrate, where light is transmitted through the glass substrate.

20 [0004] However, high precision fineness and positional alignment are difficult to achieve in methods featuring the use of a physical mask. In addition, the process is complicated in cases of separate cathode walls because an etching process is used to form the separate cathode walls.

[0005] Furthermore, the penetration through the glass substrate results in outgoing radiation, and thus in greater light leakage in the direction of the substrate plane, allowing only 20% of the total light emission to be used.

25

DISCLOSURE OF THE INVENTION

[0006] An object of the present invention is to provide a method for the extremely simple patterning of electrodes and light emitting layers in methods for manufacturing organic EL display devices, and to provide such a method in
30 which all the light emission is radiated outward in the direction of the visual field without being wasted.

[0007] Means 1 for solving the problem: The method for manufacturing an organic EL display device in the present invention is a method for manufacturing an organic EL display device which is used in simple matrix drives, characterized in that a light-heat conversion layer and heat-propagating layer are formed on a film, a cathode layer is then formed, a light emitting layer is then formed thereon, a positive hole-injecting layer is then formed thereon, the film on
35 which these multiple layers have been formed is then placed in contact with a substrate with a stripe-patterned ITO, the aforementioned multiple layers are transferred onto the substrate by irradiating the other side of the film with a laser in such a way as to form the shape of the cathode, the film is then removed, a drive mechanism is connected to the substrate onto which the aforementioned multiple layers have been transferred, and a sealing process is carried out. This structure allows cathodes which are extremely unstable and difficult to pattern to be readily patterned simultaneously
40 with the transfer of the organic EL layer by laser.

[0008] Means 2 for solving the problem: The method for manufacturing an organic EL display device in the present invention is a method for manufacturing an organic EL display device which is used in simple matrix drives, characterized in that a light-heat conversion layer and heat-propagating layer are formed on a film, a cathode layer is then formed, an electroluminescent adhesive layer is then formed thereon, the film on which these multiple layers have been
45 formed is then placed in contact with a substrate with a stripe-patterned ITO, the aforementioned multiple layers are transferred onto the substrate by irradiating the other side of the film with a laser in such a way as to form the shape of the cathode, the film is then removed, a drive mechanism is connected to the substrate onto which the multiple layers have been transferred, and a sealing process is carried out. This structure allows cathodes with a simple structure, which are extremely unstable and difficult to pattern, to be readily patterned simultaneously with the transfer of the
50 organic EL layer by laser.

[0009] Means 3 for solving the problem: This is characterized in that an electron-injecting layer is formed between the cathode layer and light emitting layer of the first means for solving the problem or between the cathode layer and the electroluminescent adhesive layer of the second means for solving the problem. This allows the luminous efficiency to be improved in the aforementioned structures.

55 [0010] Means 4 for solving the problem: The method for manufacturing an organic EL display device that is used in simple matrix drives is characterized in that a light-heat conversion layer and heat-propagating layer are formed on a film, an anode layer is then formed, a positive hole-injecting layer is then formed thereon, a light emitting layer is then formed thereon, an electron-injecting adhesive layer is then formed thereon, the film on which these multiple layers

have been formed is then placed in contact with a substrate with a patterned cathode, the other side of the film is irradiated with a laser in such a way as to form the shape of the cathode, the film is then removed, a drive mechanism is connected to the substrate onto which the aforementioned multiple layers have been transferred, and a sealing process is carried out. This structure allows cathodes which are difficult to pattern to be readily patterned by means of a laser or the like after being formed on a glass substrate, and also allows anodes to be patterned simultaneously during the subsequent transfer of the organic EL layer. This structure also allows light to be directly transmitted to the outside without passing through the glass substrate from the organic light emitting layer, so that no light is lost, resulting in better brightness.

[0011] Means 5 for solving the problem: The method for manufacturing an organic EL display device that is used in simple matrix drives is characterized in that a light-heat conversion layer and heat-propagating layer are formed on a film, an anode layer is then formed, a positive hole-injecting layer is then formed thereon, an electroluminescent adhesive layer is then formed thereon, the film on which these multiple layers have been formed is then placed in contact with a substrate with a patterned cathode, the other side of the film is irradiated with a laser in such a way as to form the shape of the cathode, the film is then removed, a drive mechanism is connected to the substrate onto which the aforementioned multiple layers have been transferred, and a sealing process is carried out.

[0012] This structure allows cathodes which are difficult to pattern to be readily patterned by means of a laser or the like after being formed on a glass substrate, and also allows anodes to be patterned simultaneously during the subsequent transfer of the organic EL layer. The manufacturing process is also simplified because the adhesive layer also has a light-emitting function. This structure also allows light to be directly transmitted to the outside without passing through the glass substrate from the organic light emitting layer, so that no light is lost, resulting in better brightness.

[0013] Means 6 for solving the problem: This is characterized in that the aforementioned light emitting layer or electroluminescent adhesive layer is formed by applying luminescent substances emitting different-colored light by means of an ink jet head. This means allows different-colored light emitting layers to be readily formed on the film, thereby allowing a colored simple matrix display to be produced with extreme ease.

[0014] Means 7 for solving the problem: This is characterized in that means for ink separation between color regions is implemented before said light emitting layer or electroluminescent adhesive layer is applied by an ink jet head. This allows the light emitting layer to be formed in the form of stripes without staining adjacent picture elements

BRIEF DESCRIPTION OF THE DRAWINGS

[0015]

Fig. 1 is a cross section illustrating a step for manufacturing the organic EL display device in Embodiment 1.

Fig. 2 is a cross section illustrating a step for manufacturing the organic EL display device in Embodiment 1.

Fig. 3 is a cross section illustrating a step for manufacturing the organic EL display device in Embodiment 1.

Fig. 4 is a cross section illustrating a step for manufacturing the organic EL display device in Embodiment 1.

Fig. 5 is a cross section illustrating a step for manufacturing the organic EL display device in Embodiment 1.

Fig. 6 is a cross section illustrating a step for manufacturing the organic EL display device in Embodiment 1.

Fig. 7 is a cross section illustrating a step for manufacturing the organic EL display device in Embodiment 1.

Fig. 8 is a cross section of the organic EL display device in Embodiment 3.

Fig. 9 is a cross section illustrating a step for manufacturing the organic EL display device in Embodiment 4.

Fig. 10 is a cross section illustrating a step for manufacturing the organic EL display device in Embodiment 4.

Fig. 11 is a cross section illustrating a step for manufacturing the organic EL display device in Embodiment 4.

Fig. 12 is a cross section illustrating a step for manufacturing the organic EL display device in Embodiment 4.

Fig. 13 is a cross section illustrating a step for manufacturing the organic EL display device in Embodiment 4.

Fig. 14 is a cross section illustrating a step for manufacturing the organic EL display device in Embodiment 4.

Fig. 15 is a cross section illustrating a step for manufacturing the organic EL display device in Embodiment 4.

Fig. 16 is a cross section illustrating a step for manufacturing the organic EL display device in Embodiment 4.

Fig. 17 is a cross section illustrating a step for manufacturing the organic EL display device in Embodiment 4.

Fig. 18 is a cross section illustrating a step for manufacturing the organic EL display device in Embodiment 4.

Fig. 19 is a cross section illustrating a step for manufacturing the organic EL display device in Embodiment 5.

Fig. 20 is a cross section illustrating a step for manufacturing the organic EL display device in Embodiment 5.

Fig. 21 is a cross section illustrating a step for manufacturing the organic EL display device in Embodiment 5.

Fig. 22 is a cross section illustrating a step for manufacturing the organic EL display device in Embodiment 5.

Fig. 23 is a cross section illustrating a step for manufacturing the organic EL display device in Embodiment 5.

Fig. 24 is a cross section illustrating a step for manufacturing the organic EL display device in Embodiment 5.

Fig. 25 is a cross section illustrating a step for manufacturing the organic EL display device in Embodiment 5.

Fig. 26 is a cross section illustrating a step for manufacturing the organic EL display device in Embodiment 5.

BEST MODE FOR CARRYING OUT THE INVENTION

Embodiment 1

5 **[0016]** This embodiment is an example of a method for manufacturing an organic EL display device that is used in simple matrix drives, wherein a light-heat conversion layer and heat-propagating layer are formed on a film, a cathode layer is then formed, a light emitting layer is then formed thereon, a positive hole-injecting layer is then formed thereon, the film on which these multiple layers have been formed is then placed in contact with a substrate with a stripe-patterned ITO, the aforementioned multiple layers are transferred onto the substrate by irradiating the other side of the film with a laser in such a way as to form the shape of the cathode, the film is then removed, a drive mechanism is connected to the substrate onto which the aforementioned multiple layers have been transferred, and a sealing process is carried out. Figs. 1 through 6 are simple cross sections depicting the method for manufacturing the organic EL display device in the present invention.

10 **[0017]** First, a thermosetting epoxy resin in which carbon particles had been mixed was coated to a thickness of 5 microns and cured at room temperature as a layer 2 for converting laser light to heat on a base film 1 comprising a 0.1 mm thick polyethylene terephthalate film. Then, a polymethylstyrene film was formed when coated to a thickness of 1 micron as a heat propagating and release layer 3, and aluminum:lithium (10:1) was deposited to a thickness of 200 nm as a cathode layer 4 on the surface (Fig. 1).


15 **[0018]** Alq3 was then deposited to a thickness of 70 nm as the light emitting layer (Fig. 2).

20

25

30


35



40 **[0019]** A mixture of NPD and polyvinyl carbazol was then dissolved in solvent, and was coated and dried to a thickness of 60 nm as the positive hole-injecting adhesive layer 6 (Fig. 3).

45

50



55 **[0020]** The resulting film was then placed in contact with a transparent glass substrate 8 with a patterned ITO having 256 stripes (Fig. 4).

[0021] A pattern of 64 stripes was then produced with a 13 W YAG laser 9 on the film side so as to intersect the striped pattern of the ITO (Fig. 5).

[0022] The film was then removed, giving an organic EL substrate with 256 × 64 picture elements having the structure depicted in Fig. 6.

[0023] Drivers 14 and 15 and a controller 16 were then connected to the organic EL substrate 11, as shown in Fig. 7, a transparent protective substrate was placed in contact with UV setting sealant 13, and the protective substrate was cured and sealed by irradiation with UV rays. Moving image display could thus be achieved with the input of drive power and signals to the display device thus obtained.

[0024] General resins such as polycarbonates and polyether sulfones can also be used in addition to polyesters as the transfer film used in this embodiment.

[0025] Any material that can efficiently convert laser light to heat may similarly be used in addition to carbon-kneaded resins as the material for the light-heat conversion layer used in this embodiment.

[0026] Any low melting point (preferably around 100°C) material capable of withstanding the production of heat during the formation of the electrodes can similarly be used in addition to those indicated here as the heat propagating layer used in this embodiment.

[0027] Aluminum, lithium, magnesium, calcium, alloys thereof, halogenated compounds, and the like can be used as the material for forming the cathode in this embodiment.

[0028] Metal complexes such as quinoline, metal complexes such as azomethine, conjugated low molecule weight species and conjugated high molecular weight species, or any other such organic EL materials can be used as the light-emitting material used in this embodiment. The method for forming the film is not limited to deposition. The film can also be formed when the material is coated after being dissolved in a solvent.

[0029] In terms of the light emitting layer and anode, any material capable of injecting positive holes into the light emitting layer, such as triphenylamine derivatives, porphin compounds, polyaniline and its derivatives, and polythiophene and its derivatives, can be used in addition to NPD as the positive hole-injecting material used in this embodiment.


[0030] Any resin that does not hamper positive hole injection, that can be melted by heat from laser light, and that has excellent adhesion on ITO and glass can be used as the material used for the adhesive layer in this embodiment.

[0031] Thermosetting resins other than UV setting resin can similarly be used as the sealant used in this embodiment.

Embodiment 2

[0032] This embodiment is an example of a method for manufacturing an organic EL display device that is used in simple matrix drives, wherein a light-heat conversion layer and heat-propagating layer are formed on a film, a cathode layer is then formed, an electroluminescent adhesive layer is then formed thereon, the film on which these multiple layers have been formed is then placed in contact with a substrate with a stripe-patterned ITO, the aforementioned multiple layers are transferred onto the substrate by irradiating the other side of the film with a laser in such a way as to form the shape of the cathode, the film is then removed, a drive mechanism is connected to the substrate onto which the multiple layers have been transferred, and a sealing process is carried out.

[0033] A light-heat conversion layer and heat propagating layer cathode were first formed on a base film in the same manner as in the first embodiment, and MEH-PPV was then made into a film in the form of a chloroform solution and dried to a thickness of 70 nm as the electroluminescent adhesive layer.




[0034] The resulting film was then placed in contact with a transparent glass substrate with a patterned ITO in the same manner as in the first embodiment, and a driver circuit was mounted and sealed, giving an organic EL display device.

[0035] Moving image display could thus be achieved with the input of drive power and signals to the display device thus obtained.

Embodiment 3

[0036] This embodiment is an example of an electron-injecting layer formed between the cathode and light emitting layer in the first embodiment. Fig. 8 is a simple cross section of the organic EL display device in this embodiment. After the cathode in Embodiment 1 had been formed, Znq2



was deposited to a thickness of 20 nm as an electron-injecting layer 10. The light emitting layer and other layers thereafter were then formed in the same manner as in Embodiment 1, giving an organic EL display device.

[0037] The organic EL display device in Embodiment 1 had a luminous efficiency of 21 m/W, whereas this embodiment had a luminous efficiency of 2.51 m/W.

[0038] In terms of the light emitting layer and anode, any material capable of positive hole injection, such as polyphenylene vinylene derivatives, organometal complexes such as Alq3, and the like, can be used in addition to NPD as the electron-injecting material used in this embodiment. Any method that does not penetrate the cathode can be used as the method for forming the film.

[0039] This embodiment can similarly be used in Embodiment 2.

Embodiment 4

[0040] This embodiment is an example of a method for manufacturing an organic EL display device that is used in simple matrix drives, wherein a light-heat conversion layer and heat-propagating layer are formed on a film, an anode layer is then formed, a positive hole-injecting layer is then formed thereon, a light emitting layer is then formed thereon, an electron-injecting adhesive layer is then formed thereon, the film on which these multiple layers have been formed is then placed in contact with a substrate with a patterned cathode, the other side of the film is irradiated with a laser in such a way as to form the shape of the cathode, the film is then removed, a drive mechanism is connected to the substrate onto which the aforementioned multiple layers have been transferred, and a sealing process is carried out. Figs. 9 through 14 are simple cross sections depicting the method for manufacturing the organic EL display device in the present invention.

[0041] First, the light-heat conversion layer 2 and heat propagating layer 3 given in Embodiment 1 were formed on a base film 1 comprising a 1 mm thick polycarbonate film, and indium tin oxide was formed by sputtering to a thickness of 200 nm as an anode layer 7 (Fig. 9).


MTDATA

5

10

15

20



was then deposited to a thickness of 15 nm as the positive hole-injecting layer 17, and NPD was then deposited to a thickness of 20 nm. Alq3 was then deposited to a thickness of 70 nm as the light emitting layer 5 (Fig. 10).

25 [0042] A chloroform solution of PPV was then applied to a thickness of 60 nm as an electron-injecting adhesive layer 18 (Fig. 11).

[0043] The resulting film was then placed in contact with a transparent glass substrate having an aluminum and lithium alloy cathode patterned with 256 stripes by laser (Fig. 12).

30 [0044] A pattern of 64 stripes was then produced with W YAG laser 9 on the film side so as to intersect the striped pattern of the ITO (Fig. 13).

[0045] The film was then removed, giving the organic EL substrate with 256 × 64 picture elements having the structure depicted in Fig. 14.

35 [0046] Drivers and a controller were then connected to the organic EL substrate, as shown in Fig. 7, a transparent protective substrate was placed in contact with an epoxy thermosetting sealant, and the protective substrate was cured and sealed at room temperature. Moving image display could thus be achieved with the input of drive power and signals to the display device thus obtained. The luminous efficiency was 31 m/W.

[0047] The same materials and methods given in Embodiment 1 can be used in this embodiment as well.


Embodiment 5

40

[0048] This embodiment is an example of a method for manufacturing an organic EL display device that is used in simple matrix drives, wherein a light-heat conversion layer and heat-propagating layer are formed on a film, an anode layer is then formed, a positive hole-injecting layer is then formed thereon, an electroluminescent adhesive layer is then formed thereon, the film on which these multiple layers have been formed is then placed in contact with a substrate with a patterned cathode, the other side of the film is irradiated with a laser in such a way as to form the shape of the cathode, the film is then removed, a drive mechanism is connected to the substrate onto which the aforementioned multiple layers have been transferred, and a sealing process is carried out.

45 [0049] Figs. 15 through 18 are simple cross sections depicting the method for manufacturing the organic EL display device in the present invention. An anode and positive hole-injecting layer were formed on a base film in the same manner as in Embodiment 3. A chloroform solution of PPV

55



was then coated and dried to a thickness of 60 nm as an electroluminescent adhesive layer 19 (Fig. 15).

[0050] The resulting film was then placed in contact with a transparent glass substrate 8 having an aluminum and lithium alloy cathode 4 patterned with 256 stripes by laser (Fig. 16).

[0051] A pattern of 64 stripes was then produced with a 13 W YAG laser 9 on the film side so as to intersect the striped pattern of the ITO (Fig. 17).

[0052] The film was then removed, giving the organic EL substrate with 256×64 picture elements having the structure depicted in Fig. 18.

[0053] Drivers and a controller were then connected to the organic EL substrate, as shown in Fig. 7, a transparent protective substrate was placed in contact with a UV setting sealant, and the protective substrate was cured and sealed at room temperature by being irradiated with UV rays from behind. Moving image display could thus be achieved with the input of drive power and signals to the display device thus obtained. The luminous efficiency was 3.51 m/W.


[0054] The same materials and methods given in Embodiment 1 can be used in this embodiment as well.

Embodiment 6

[0055] This embodiment is an example of luminescent substances emitting red, green, and blue light, which are dissolved and applied using an ink jet head to form the aforementioned light emitting layer during the formation of the light emitting layer in Embodiment 4. Figs. 19 through 25 are simple cross sections depicting the method for manufacturing the organic EL display device in the present invention.

[0056] Layers were first prepared in the same manner as in Embodiment 4 up to the formation of the cathode on the film.

[0057] Then, as shown in Fig. 19, a xylene solution of MEH-PPV was applied and dried in the form of a stripe by an ink jet head 20 to form a red-light emitting layer 21. Then, as shown in Fig. 20, a xylene solution of PPV was applied and dried in the form of a stripe by the ink jet head to form a green light emitting layer 22 next to the above layer. Then, as shown in Fig. 21, a xylene solution of a fluorene compound



was applied and dried in the form of a stripe by the ink jet head to form a blue light emitting layer 23 between the aforementioned MEH-PPV and PPV derivatives.

[0058] Then, PPV was dissolved in solvent and was coated and dried to a thickness of 60 nm an electron-injecting adhesive layer 18 (Fig. 22).

[0059] The resulting film was then placed in contact with a transparent glass substrate 8 having an aluminum and lithium alloy cathode 4 patterned with 256 stripes by laser, where the stripes of the light emitting layers were aligned with the stripes of the cathode (Fig. 23).

[0060] A pattern of 64 stripes was then produced with a YAG laser 7 on the film side so as to intersect the striped pattern of the cathode 2 (Fig. 24).

[0061] The film was then removed, giving the organic EL substrate with 256×64 picture elements having the structure depicted in Fig. 25.

[0062] Drivers and a controller were then connected to the organic EL substrate, as shown in Fig. 7, a transparent protective substrate was placed in contact with an epoxy thermosetting sealant to the anode, and moving image display

could be achieved with the input of drive power and signals.

[0063] The same materials and manufacturing conditions given in Embodiment 4 can be used in this embodiment as well.

[0064] This embodiment was carried out with the structure given in Embodiment 4, but it can similarly be applied in the preparation of the light emitting layers or electroluminescent adhesive layers in the other embodiments.

Embodiment 7

[0065] This embodiment is an example of the formation of partition walls in the light emitting layer prior to the formation of the cathode on the film. As shown in Fig. 26, partition walls 24 were printed in the widthwise direction between the colored light emitting layers by means of screen printing using thermosetting polyimide, and were heated and cured on the film used in Embodiment 5. An organic EL display device was then obtained in the same manner as an Embodiment 6.

[0066] The use of the resulting display device for color display allowed extremely bright display to be achieved without any color confusion.

[0067] The materials and methods used to form partition walls are not limited to those given here. Any other material and method capable of manufacturing the structure depicted in Fig. 26 can be used.

[0068] Although a partition wall structure was used as the element means between the colored light emitting layers here, ink may also be applied between picture elements following the formation of the electrode.

INDUSTRIAL APPLICABILITY

[0069] Although it has been extremely difficult to pattern chemically unstable cathodes in the past, the present application allows such cathodes to be readily patterned. The elemental structure can be the reverse of conventional structures, making it possible to suppress the loss of light that is caused by the effects of moving light when emitted light passes through a glass substrate. An organic EL display with high luminous efficiency can thus be inexpensively produced by a simple method.

Claims

1. A method for producing an organic EL display device used in simple matrix drives, wherein said method for producing an organic EL display device is characterized by comprising the steps of:

forming a light-heat conversion layer and heat-propagating layer on a film;
forming a cathode layer;
forming a light emitting layer thereon;
forming a positive hole-injecting layer thereon;
placing the film on which these multiple layers have been formed in contact with a substrate with a stripe-patterned ITO;
transferring said multiple layers onto the substrate by irradiating the other side of the film with a laser in such a way as to form the shape of the cathode;
removing the film;
connecting a drive mechanism to the substrate onto which said multiple layers have been transferred and carrying out a sealing process.

2. A method for producing an organic EL display device used in simple matrix drives, wherein said method for producing an organic EL display device is characterized by comprising the steps of:

forming a light-heat conversion layer and heat-propagating layer on a film;
forming a cathode layer ;
forming an electroluminescent adhesive layer thereon;
placing the film on which these multiple layers have been formed in contact with a substrate with a stripe-patterned ITO;
transferring said multiple layers onto the substrate by irradiating the other side of the film with a laser in such a way as to form the shape of the cathode;
removing the film;
connecting a drive mechanism to the substrate onto which the multiple layers have been transferred and carrying out a sealing process.

3. The method for manufacturing an organic EL display device according to Claim 1 or 2, characterized in that an electron-injecting layer is formed between said cathode layer or said electroluminescent adhesive layer and said light emitting layer.

5 4. A method for producing an organic EL display device used in simple matrix drives, wherein said method for producing an organic EL display device is characterized by comprising the steps of:

forming a light-heat conversion layer and heat-propagating layer on a film;
forming an anode layer;
10 forming a positive hole-injecting layer thereon;
forming a light emitting layer thereon;
forming an electron-injecting adhesive layer thereon;
placing the film on which these multiple layers have been formed in contact with a substrate with a patterned cathode;
15 irradiating the other side of the film with a laser in such a way as to form the shape of the cathode;
removing the film;
connecting a drive mechanism to the substrate onto which said multiple layers have been transferred; and carrying out a sealing process.

20 5. A method for producing an organic EL display device used in simple matrix drives, wherein said method for producing an organic EL display device is characterized by comprising the steps of:

forming a light-heat conversion layer and heat-propagating layer on a film;
forming an anode layer;
25 forming a positive hole-injecting layer thereon;
forming an electroluminescent adhesive layer thereon;
placing the film on which these multiple layers have been formed in contact with a substrate with a patterned cathode;
irradiating the other side of the film with a laser in such a way as to form the shape of the cathode;
30 removing the film;
connecting a drive mechanism to the substrate onto which said multiple layers have been transferred; and carrying out a sealing process.

35 6. The method for manufacturing an organic EL display device according to Claim 1, 2, 4, or 5, characterized in that said light emitting layer or electroluminescent adhesive layer is formed by applying luminescent substances emitting different-colored light by means of an ink jet head.

40 7. The method for manufacturing an organic EL display device according to Claim 6, characterized in that means for ink separation between color regions is implemented before said light emitting layer or electroluminescent adhesive layer is applied by an ink jet head.

45

50

55

Fig. 1




Fig. 2




Fig. 3




Fig. 4




Fig. 5




Fig. 6




Fig. 7




Fig. 8




Fig. 9




Fig. 10




Fig. 11




Fig. 12




Fig. 13




Fig. 14




Fig. 15




Fig. 16




Fig. 17




Fig. 18




Fig. 19




Fig. 20




Fig. 21




Fig. 22




Fig. 23




Fig. 24




Fig. 25





Fig. 26



INTERNATIONAL SEARCH REPORT

International application No.

PCT/JP99/01132

A. CLASSIFICATION OF SUBJECT MATTER Int.Cl ⁶ H05B33/10 According to International Patent Classification (IPC) or to both national classification and IPC		
B. FIELDS SEARCHED Minimum documentation searched (classification system followed by classification symbols) Int.Cl ⁶ H05B33/10 Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched Jitsuyo Shinan Koho 1926-1996 Toroku Jitsuyo Shinan Koho 1994-1999 Kokai Jitsuyo Shinan Koho 1971-1999 Jitsuyo Shinan Toroku Koho 1996-1999 Electronic data base consulted during the international search (name of data base and, where practicable, search terms used)		
C. DOCUMENTS CONSIDERED TO BE RELEVANT		
Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
P, X	JP, 10-208881, A (Sansei Denkan K.K.), 7 August, 1998 (07. 08. 98) (Family: none)	1-5
A	JP, 10-12377, A (Seiko Epson Corp.), 16 January, 1998 (16. 01. 98) (Family: none)	6, 7
<input type="checkbox"/> Further documents are listed in the continuation of Box C. <input type="checkbox"/> See patent family annex.		
* Special categories of cited documents: "A" document defining the general state of the art which is not considered to be of particular relevance "E" earlier document but published on or after the international filing date "L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reasons (as specified) "U" document referring to an oral disclosure, use, exhibition or other means "P" document published prior to the international filing date but later than the priority date claimed "I" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention "X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone "Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art "&" document member of the same patent family		
Date of the actual completion of the international search 31 May, 1999 (31. 05. 99)		Date of mailing of the international search report 8 June, 1999 (08. 06. 99)
Name and mailing address of the ISA/ Japanese Patent Office		Authorized officer
Facsimile No.		Telephone No.

Form PCT/ISA/210 (second sheet) (July 1992)

**This Page is Inserted by IFW Indexing and Scanning
Operations and is not part of the Official Record**

BEST AVAILABLE IMAGES

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images include but are not limited to the items checked:

- ☐ **BLACK BORDERS**
- ☐ **IMAGE CUT OFF AT TOP, BOTTOM OR SIDES**
- ☒ **FADED TEXT OR DRAWING**
- ☒ **BLURRED OR ILLEGIBLE TEXT OR DRAWING**
- ☐ **SKEWED/SLANTED IMAGES**
- ☐ **COLOR OR BLACK AND WHITE PHOTOGRAPHS**
- ☐ **GRAY SCALE DOCUMENTS**
- ☐ **LINES OR MARKS ON ORIGINAL DOCUMENT**
- ☐ **REFERENCE(S) OR EXHIBIT(S) SUBMITTED ARE POOR QUALITY**
- ☐ **OTHER:** _____

IMAGES ARE BEST AVAILABLE COPY.

As rescanning these documents will not correct the image problems checked, please do not report these problems to the IFW Image Problem Mailbox.